

APPENDIX B FINISH CHART

| FINISH PROPERTIES | | | | | | | |
|-------------------------|------------------------|-----------------|------------------------------------|-----------------------|----------------|-------------|--------------------------|
| PRODUCT | Respiratory Protection | Number of Coats | Drying Time | Color | Sheen | Odor | Flammability |
| Oil-modified Urethane | Required | 2-3 | Slow | Amber | Satin to Gloss | Moderate | Combustible |
| Water-borne Urethane | Required | 2-4 | Fast | Clear to Amber | Satin to Gloss | Mild | Non-combustible |
| Moisture-Cured Urethane | Required | 2-3 | Slow to Fast (depends on humidity) | Clear to Dark Amber | Satin to Gloss | Strong | Combustible to Flammable |
| Conversion Varnish | Required | 2-3 | Fast | Clear to Slight Amber | Satin to Gloss | Very Strong | Combustible |
| Wax | Optional | 1-3 | Fast | Slight Amber | Wax Luster | Mild | Combustible |